

Paracord 550

Art. Number : 422 322 004

Description :

Note :

Machine No. : 0500-11241

Test Name : PEVNOST LAN

Test Type : Tensile


Test Date : 17.2.2015 11:14

Test Speed : 250,000 mm/min

Pretension : 100,000 N

Sample Length : 500,000 mm

Test No	Force @ Peak (kN)	Force @ Peak (lbf)	Elong. @ Break (mm)	Strain @ Break (%)	Energy to Peak (N.m)
1	3,035	682,295	159,399	31,880	230,943
2	3,255	731,753	168,545	32,924	264,303
3	3,138	705,450	163,218	31,935	246,263
Min	3,035	682,295	159,399	31,880	230,943
Mean	3,143	706,500	163,721	32,246	247,169
Median	3,138	705,450	163,218	31,935	246,263
Max	3,255	731,753	168,545	32,924	264,303



— Test 1 — Test 2 — Test 3