


Kód výrobku : 522 165 060
 NÁZEV : gomolano 6 mm
 POZNÁMKA : černé

Machine No. : 0500-11241
 Test Name : PEVNOST GUMOLAN
 Test Type : Tensile
 Test Date : 4.2.2015 15:13
 Test Speed : 250,000 mm/min
 Pretension : 10,000 N
 Sample Length : 500,000 mm

Test No	Force @ Peak (kN)	Force @ Peak (lbf)	Elong. @ Break (mm)	Strain @ Break (%)	Energy to Peak (N.m)
1	1,251	281,236	961,000	141,372	332,443
2	1,312	294,949	1073,450	155,112	440,824
Min	1,251	281,236	961,000	141,372	332,443
Mean	1,282	288,093	1017,225	148,242	386,634
Max	1,312	294,949	1073,450	155,112	440,824
S.D.	0,043	9,697	79,514	9,716	76,636
C. of V.	3,366	3,366	7,817	6,554	19,821
L.C.L.	0,894	200,970	302,822	60,950	-301,918
U.C.L.	1,669	375,215	1731,628	235,535	1075,185



— Test 1 — Test 2