


522 166 080

Kód výrobku : 522 166 080
 NÁZEV : gomolana pr. 8 mm
 POZNÁMKA : černé

Machine No. : 0500-11241
 Test Name : PEVNOST GUMOLAN
 Test Type : Tensile
 Test Date : 10.3.2017 13:40
 Test Speed : 250,000 mm/min
 Pretension : 10,000 N
 Sample Length : 500,000 mm

Test No	Force @ Peak (kN)	Force @ Peak (lbf)	Elong. @ Break (mm)	Strain @ Break (%)	Energy to Peak (N.m)
1	0,409	91,947	914,810	178,185	110,215
2	0,465	104,536	979,713	195,410	135,454
3	0,419	94,195	945,709	188,959	116,473
4	0,407	91,497	906,919	181,209	106,362
Min	0,407	91,497	906,919	178,185	106,362
Mean	0,425	95,544	936,788	185,941	117,126
Median	0,414	93,071	930,260	185,084	113,344
Max	0,465	104,536	979,713	195,410	135,454



— Test 1 — Test 2 — Test 3 — Test 4